

Sheath-Core nonofilament High-strength polyester, High- fusible polyester

Fabric No.	Mesh count	Diameter	Mesh opening	Opening area	Thickness
	inch	micron	micron	%	micron
LX 60SS	60	55	370	76	80
LX 70SS	70	55	308	72	80
LX 80SS	80	55	265	68	80
LX 100SS	100	48	206	62	80
LX 100S	100	55	199	61	90
LX 120S	120	48	164	62	80
LX 135S	135	48	140	58	80
LX 150S	150	48	121	51	80
LX 180S	180	48	93	44	80

© Calculations of the mesh opening, opening area, and ink volume are based on the number of mesh and the diameter.

※ Thickness is a reference value