TG

Polyester Mesh

Multifilament × Multifilament : 600~861 Monofilament × Multifilament : 1000~230

Fabric No.	Type of weave	Mesh count	Diameter	Mesh opening	Opening area	Thickness	Ink volume	Available width			
								cm	115	135	165
		/inch	μm	μm	%	μm	cm3/m2	inch	45	53	65
600	PW	60×60	83 × 83	340	65	89	57				
700	PW	70 × 70	83 × 83	280	59	95	57				
800	PW	80 × 80	83 × 83	235	55	100	55				
861	PW	86 × 84	45 × 83	235	61	76	47				
1000	PW	100 × 97	48 × 83	192	55	84	47			•	
1200	PW	118 × 116	48 × 83	152	48	86	42		•	•	
1350	PW	132 × 130	48 × 83	128	43	86	38		•	•	
1500	PW	147 × 140	48 × 83	112	39	89	36		•	•	•
1600	PW	158 × 150	48 × 67	108	42	80	34				
1800	PW	178 × 168	48 × 67	89	37	75	28				
2000	PW	197 × 176	48 × 67	79	34	74	25				
2300	PW	225 × 190	48 × 67	66	29	75	21				



Polyester Mesh (Multifilament)

SNittoku

Fabric No.	Type of weave	Mesh count	Diameter	Mesh opening	Opening area	Thickness	Ink volume	Available width			
								cm	107	132	168
		/inch	μm	μm	%	μm	cm3/m2	inch	42	52	66
6	PW	70 × 70	130	233	41	139	57				
8	PW	78 × 83	130	186	35	135	47				
10	PW	110 × 106	95	140	35	101	36				
12	PW	128 × 124	95	107	28	102	29				
16	PW	148 × 150	83	87	26	96	25				

Blank=Ordered product (Some products may be available. Please feel free to contact us.)

- Calculations of the mesh opening, opening area, and ink volume are based on the number of mesh and the diameter.
- Type of weave indicates PW=plain weaving and TW=twill weaving.
- The specifications are standard values and not guaranteed values.
- \blacksquare Please note that these specifications are subject to change without prior notice for improvements.

Available width (status of production availability

 ⁼ Regular product (Products are manufactured based on past records, but this does not quarantee future manufacturing conditions.)